

## STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Number of Tests ..... 20  
 % Crush (5mm & Above).... 94.7%  
 Moisture Content ..... N/A

Product Number..... 20 S - Drain Rock  
 Type of Sample ..... Production  
 Source ..... Windfall

SCREEN SIZE mm	***** PERCENT PASSING *****		
	AVERAGE	MINIMUM	MAXIMUM
25.0	100.0		
20.0	96.5	100	
16.0	45.1		
12.5	32.4		
10.0	9.9	45	75
5.0	3.0		15
2.5	1.5		5
1.25	1.2		
630μ	1.2		
315μ	1.1		
160μ	1.1		
80μ	1.0		

### AGGREGATE GRADATION

