

STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Test Number 334
% Crush % 95.9%
Moisture Content N/A

Product Number..... Class 1&2 CN Ballast
Type of Sample Production
Source Windfall

SCREEN SIZE mm	***** PERCENT PASSING *****		
	SAMPLE	MINIMUM	MAXIMUM
63.0	99.9	100.0	
50.0	88.2	75.0	95.0
37.5	45.8	35.0	65.0
25.0	11.0	0.0	25.0
20.0	3.0	0.0	4.0
16.0	3.0		
12.5	3.0		
10.0	3.0		
5.0	3.0		
2.5	3.0		
1.25	3.0		
630μ	3.0		
315μ	3.0		
160μ	3.0		
80μ	0.3	0.0	1.0

