

STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Number of Tests 103
 % Crush (5mm & Above).... 94.7%
 Moisture Content 2.84%

Product Number..... Des 2-20
 Type of Sample Production
 Source Windfall

SCREEN	***** PERCENT PASSING *****		
SIZE mm	AVERAGE	MINIMUM	MAXIMUM
25.0	100.0		
20.0	99.2	100	
16.0	86.9	84	94
12.5	74.1		
10.0	65.1	63	86
5.0	46.4	40	67
2.5	35.7		
1.25	31.2	20	43
630μ	27.3	14	34
315μ	18.4	9	26
160μ	9.9	5	18
80μ	6.1	2	10

AGGREGATE GRADATION

