

STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Number of Tests 79
 Moisture Content..... 3.49%

Product Number..... Des 2 - 40
 Type of Sample Production
 %Crush 86.19%

SCREEN SIZE mm	***** PERCENT PASSING *****		
	SAMPLE	MINIMUM	MAXIMUM
63.0	100.0		
50.0	100.0		
40.0	99.9	97	100
25.0	84.5	70	94
20.0	66.8		
16.0	59.9	55	85
12.5	52.3		
10.0	47.1	44	74
5.0	35.8	32	62
2.5	28.8		
1.25	25.7	17	43
630μ	22.8	12	34
315μ	14.5	8	26
160μ	7.8	5	18
80μ	4.8	2	10

