

STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Number of Tests 446
 % Crush (5mm & Above)....96.3%
 Moisture Content2.37%

Product Number.....Des 3-20
 Type of Sample Production
 Source Windfall

SCREEN	***** PERCENT PASSING *****		
SIZE mm	AVERAGE	MINIMUM	MAXIMUM
25.0	100.0		
20.0	99.3	100	
16.0	89.7	84	95
12.5	76.0	60	90
10.0	65.9	50	84
5.0	46.8	37	62
2.0	34.8	26	50
1.25	30.7	19	43
630μ	26.7	14	34
400μ	20.7	11	28
160μ	9.4	6	18
80μ	5.7	2	10

AGGREGATE GRADATION

