

STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Test Number 12
 % Crush % 62.9%
 Moisture Content 3.53%

Product Number..... Des 6 - 80
 Type of Sample Production
 Source Windfall

SCREEN SIZE mm	***** PERCENT PASSING *****		
	SAMPLE	MINIMUM	MAXIMUM
80.0	100.0	100	
50.0	92.7	55	100
40.0	74.6		
25.0	45.6	38	100
20.0	37.6		
16.0	33.9	32	85
12.5	30.3		
10.0	28.3		
5.0	23.6	20	65
2.5	21.0		
1.25	19.3		
630μ	17.1		
315μ	9.4	6	30
160μ	4.6		
80μ	2.8	2	10

