

STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

Test Number 12
 % Crush % 83.4%
 Moisture Content 1.24%

Product Number..... Industrial Ballast
 Type of Sample Production
 Source Windfall

SCREEN SIZE mm	***** PERCENT PASSING *****		
	SAMPLE	MINIMUM	MAXIMUM
40.0	100.0	100	
37.5	98.6		
31.5	87.4	75	90
25.0	61.1	50	80
20.0	34.9	30	60
12.5	14.9	10	30
10.0	8.1		
5.0	1.1	0	3
2.5	0.7	0	1
1.25	0.6		
630μ	0.5		
315μ	0.4		
160μ	0.3		
80μ	0.2		

