

## STANDARD GENERAL INC. - AGGREGATE SIEVE ANALYSIS REPORT

*Number of Tests* ..... 261  
*% Crush (5mm & Above)*... 100.0%  
*Moisture Content*..... 0.76%

*Product Number*..... 5 S - 821000  
*Type of Sample* ..... Production  
*Source* ..... Windfall

SCREEN SIZE mm	***** PERCENT PASSING *****		
AVERAGE			
10.0	100.0	99	100
5.0	96.8	90	97
2.5	70.6		
1.25	52.6		
630μ	42.0		
315μ	29.7		
160μ	17.9		
80μ	10.6		

### AGGREGATE GRADATION

